


## Analysis of Polystyrene Standard



Column	: Inertsil SIL-100A 5 $\mu$ m 250 x 4.6 mm I.D.	Solutes	: 1. Polystyrene (0.2 mg/mL, Mp 1,020,000) 2. Polystyrene (0.2 mg/mL, Mp 115,000) 3. Polystyrene (0.2 mg/mL, Mp 9,200) 4. Polystyrene (0.2 mg/mL, Mp 950)
Column Cat. No.	: 5020-01712		
Eluent	: THF		
Flow rate	: 1.0 mL/min.		
Col. Temp.	: Ambient		
Detection	: UV 254 nm		
Injection Vol.	: 5 $\mu$ L		
Sample	:		